

HOSTAFORM® C 9021 GV1/10

HOSTAFORM®

Chemical abbreviation according to ISO 1043-1: POM Molding compound ISO 29988- POM-K, M-GNR, 02-003, GF10 POM copolymer Injection molding type, reinforced with ca. 10 % glass fibers; high resistance to thermal and oxidative degradation; reduced thermal expansion and shrinkage. UL-registration in natural and black and a thickness more than 1.5 mm as UL 94 HB, temperature index UL 746 B, electrical 105 °C, mechanical 105 °C Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1 mm. Ranges of applications: For molded parts with high strength and rigidity as well as higher hardness. FMVSS = Federal Motor Vehicle Safety Standard (USA) UL = Underwriters Laboratories (USA)

Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

Rheological properties

Melt volume-flow rate	6 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	1.4 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.1 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	4800 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	90 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4 %	ISO 527-1/-2
Flexural modulus	4500 MPa	ISO 178
Flexural strength	130 MPa	ISO 178
Flexural strain at failure	3.4 %	ISO 178
Tensile creep modulus, 1h	3700 MPa	ISO 899-1
Tensile creep modulus, 1000h	2500 MPa	ISO 899-1
Charpy impact strength, 23 °C	40 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30 °C	50 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	6.5 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30 °C	6.5 kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 358/30	170 MPa	ISO 2039-1
Poisson's ratio	0.434	

Thermal properties

Melting temperature, 10 °C/min	166 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	154 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	64 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	80 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	90 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3 mm	IEC 60695-11-10

HOSTAFORM® C 9021 GV1/10

HOSTAFORM®

UL recognition	yes	UL 94
----------------	-----	-------

Electrical properties

Relative permittivity, 100Hz	4.1	IEC 62631-2-1
Relative permittivity, 1MHz	4.1	IEC 62631-2-1
Dissipation factor, 100Hz	30 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	60 E-4	IEC 62631-2-1
Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	35 kV/mm	IEC 60243-1
Comparative tracking index	600	IEC 60112

Physical/Other properties

Humidity absorption, 2mm	0.19 %	Sim. to ISO 62
Water absorption, 2mm	0.85 %	Sim. to ISO 62
Density	1480 kg/m ³	ISO 1183

Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	200 °C
Min. melt temperature	190 °C
Max. melt temperature	210 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Hold pressure range	60 - 120 MPa
Back pressure	2 MPa

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent

Additional information

Injection molding

Preprocessing

General drying is not necessary due to low moisture absorption of the resin.

In case of bad storage conditions (water contact or condensed water) the use of a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

HOSTAFORM® C 9021 GV1/10

HOSTAFORM®

Max. Water content 0,2 %

Processing

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

Postprocessing

Conditioning e.g. moisturizing is not necessary.

Processing Notes

Pre-Drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.

Storage

The product can then be stored in standard conditions until processed.


Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Bosch	N28 BN22-X006	Natural
Bosch	N28 BN22-X006	Black
Stellantis - Chrysler	MS.50095 / CPN-5090	Black

HOSTAFORM® C 9021 GV1/10

HOSTAFORM®

Stress-strain



HOSTAFORM® C 9021 GV1/10

HOSTAFORM®

Secant modulus-strain

