

# HOSTAFORM® C 9021 GV1/30

## HOSTAFORM®

Chemical abbreviation according to ISO 1043-1: POM Molding compound ISO 29988- POM-K, M-GNR, 02-003, GF26  
POM copolymer Injection molding type, reinforced with ca 26 % glass fibers; high resistance to thermal and oxidative degradation; reduced thermal expansion and shrinkage. UL-registration for all colours and a thickness more than 1.57 mm as UL 94 HB, temperature index UL 746 B electrical 105 °C, mechanical 95 °C (tensile impact) and 100 °C (tensile).  
Burning rate ISO 3795 and FMVSS 302 < 100 mm/min and a thickness more than 1 mm thickness. Ranges of applications: For molded parts with very high strength and rigidity as well as higher hardness. FMVSS = Federal Motor Vehicle Safety Standard (USA) UL = Underwriters Laboratories (USA)

### Product information

Resin Identification	POM-GF26	ISO 1043
Part Marking Code	>POM-GF26<	ISO 11469

### Rheological properties

Melt volume-flow rate	4 cm <sup>3</sup> /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	0.6 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.0 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	9200 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	135 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.5 %	ISO 527-1/-2
Flexural modulus	7800 MPa	ISO 178
Flexural strength	160 MPa	ISO 178
Tensile creep modulus, 1h	7700 MPa	ISO 899-1
Tensile creep modulus, 1000h	5400 MPa	ISO 899-1
Charpy impact strength, 23 °C	30 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30 °C	35 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23 °C	8 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30 °C	8 kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness, H 358/30	200 MPa	ISO 2039-1
Poisson's ratio	0.392	

### Thermal properties

Melting temperature, 10 °C/min	166 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	160 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	125 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	40 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	80 E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.215 W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	6.51E-8 m <sup>2</sup> /s	ISO 22007-4
Specific heat capacity of melt	1810 J/(kg K)	ISO 22007-4

# HOSTAFORM® C 9021 GV1/30

## HOSTAFORM®

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.6 mm	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.18 mm	IEC 60695-11-10
UL recognition	yes	UL 94

### Electrical properties

Relative permittivity, 100Hz	4.3	IEC 62631-2-1
Relative permittivity, 1MHz	4.3	IEC 62631-2-1
Dissipation factor, 100Hz	30 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	60 E-4	IEC 62631-2-1
Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	40 kV/mm	IEC 60243-1
Comparative tracking index	600	IEC 60112

### Physical/Other properties

Humidity absorption, 2mm	0.17 %	Sim. to ISO 62
Water absorption, 2mm	0.9 %	Sim. to ISO 62
Density	1600 kg/m³	ISO 1183

### Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	200 °C
Min. melt temperature	190 °C
Max. melt temperature	210 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Hold pressure range	60 - 120 MPa
Back pressure	2 MPa
Ejection temperature	133 °C

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent

# HOSTAFORM® C 9021 GV1/30

## HOSTAFORM®

### Additional information

Injection molding

### Preprocessing

General drying is not necessary due to low moisture absorption of the resin.

In case of bad storage conditions (water contact or condensed water) the use of a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

Max. Water content 0,2 %

### Processing

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

### Postprocessing

Conditioning e.g. moisturizing is not necessary.

Processing Notes

### Pre-Drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.

### Storage

The product can then be stored in standard conditions until processed.

### Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
BMW	GS93016	
Bosch	N28 BN22-X010	Natural
Bosch	N28 BN22-X010	Black
Continental	TST N 055 54.10	
General Motors	GMW17968P-POM-GF25	Natural
Mercedes-Benz	DBL5403	(5401.00)
Mercedes-Benz	DBL5406	(5406.00)
Mercedes-Benz	DBL5410	(5410.00)
Mercedes-Benz	DBL5420	(5420.00)

# HOSTAFORM® C 9021 GV1/30

## HOSTAFORM®

Stellantis - Chrysler


VW Group

MS.50095 / CPN-4291

No Spec, Special Part Approval, See Your CE  
Account Manager.

Natural


### Viscosity-shear rate



# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®


Shearstress-shear rate



# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®


## Stress-strain



# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®


## Secant modulus-strain



# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®

Stress-strain (isochronous) 80°C






# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®


Creep modulus-time 80°C



# HOSTAFORM® C 9021 GV1/30

HOSTAFORM®


Creep modulus-time 85°C



# HOSTAFORM® C 9021 GV1/30

## HOSTAFORM®

Creep strain-time 85 °C



Printed: 2025-03-24

Page: 11 of 11

Revised: 2024-11-26 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.