

Zytel® HTNFR42G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Zytel® HTNFR42G30NH NC010 is a 30% glass reinforced, flame retardant high performance polyamide resin developed for improved reflow soldering performance in connector applications. It is also a PPA resin and it uses a non-halogenated flame retardant and red phosphorous free.

Product information

Resin Identification	PPA- GF30FR(40)	ISO 1043
Part Marking Code	>PPA-GF30FR(40)<	ISO 11469
Part Marking Code	>PPA-GF30FR<	SAE J1344
ISO designation	ISO 16396-PA,GF30 FR(40),M1F1GNR,S10-110	
Biobased carbon content	≥20 ^[C] %	ISO 16620-2
[C]: Calculated		

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.4 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.9 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10600 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	138 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.9 / -	%	ISO 527-1/-2
Flexural modulus	11200 / -	MPa	ISO 178
Flexural strength	220 / -	MPa	ISO 178
Charpy impact strength, 23°C	46 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7 / -	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34 / -		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	311 / *	°C	ISO 11357-1/-3
Melting temperature, first heat	315 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	80 / 50	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	276 / *	°C	ISO 75-1/-2
Ball pressure test	270 / - ^[DS]	°C	IEC 60695-10-2
RTI, electrical, 0.4mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3.0mm	130	°C	UL 746B
RTI, impact, 0.4mm	115	°C	UL 746B
RTI, impact, 1.5mm	115	°C	UL 746B
RTI, impact, 3.0mm	120	°C	UL 746B
RTI, strength, 0.4mm	125	°C	UL 746B
RTI, strength, 1.5mm	125 / *	°C	UL 746B
RTI, strength, 3.0mm	130	°C	UL 746B

[DS]: Derived from similar grade

Zytel® HTNFR42G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Glow Wire Flammability Index, 0.4mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.4mm	750 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.5mm	800 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	825 / -	°C	IEC 60695-2-13

Electrical properties

	dry/cond.		
Volume resistivity	>1E13 / -	Ohm.m	IEC 62631-3-1
Electric strength	40 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112
Comparative tracking index, 3.0mm	0 / -	PLC	UL 746A

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1 / *	%	Sim. to ISO 62
Water absorption, 2mm	2.7 / *	%	Sim. to ISO 62
Density	1450 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	6 - 8 h
Processing Moisture Content	≤0.1 %
Min. melt temperature	330 °C
Max. melt temperature	335 °C
Min. mould temperature	110 °C
Max. mould temperature	130 °C

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent, Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Lead-free soldering resistant

Additional information

Injection molding	For molding machine components, use corrosion resistant and wear resistant steel. For details please contact our representative. Limit the residence time of the resin in the machine. Use proper protective equipment and adequate ventilation.
-------------------	--

Zytel® HTNFR42G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Printed: 2025-03-27

Page: 3 of 3

Revised: 2025-01-28 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.