

Vydyne® R525J BK0722

polyamide 66



Vydyne R525J BK0722 is a black, 25% glass filled, high flow, PA66 that contains an electrically neutral heat stabilizer. It is specifically designed for electrical applications requiring high dielectric strength, low conductivity, corrosion resistance, and laser markability.

General

Additive	• Heat Stabilizer		
Features	• Chemical Resistant • Good Electrical Properties • High Strength	• Corrosion Resistant • Good Mold Release • Laser Markable	• Good Colorability • High Flow • Organic Heat Stabilized
Agency Rating	• ASTM, D4066 PA012G25	• ASTM, D6779 PA012G25	
UL File Number	• E70062		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.32	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	0.9	*	%	
Flow : 23°C, 2.00 mm	0.4	*	%	
Water Absorption				ISO 62
23°C, 24 hr	0.9	*	%	
Equilibrium, 23°C, 50% RH	2	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	8600	5500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	161	117	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.4	7	%	ISO 527-2
Flexural Modulus (23°C)	7700	5700	MPa	ISO 178
Flexural Strength (23°C)	250	150	MPa	ISO 178
Poisson's Ratio (23°C)	0.4			ISO 527-2

Impact

	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	11	12	kJ/m ²	
-30°C	10	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	65	67	kJ/m ²	

©2025 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Vydyne® R525J BK0722

polyamide 66



-30°C	55	66	kJ/m²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	10	15	kJ/m²	
-30°C	9	10	kJ/m²	

Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	245	-	°C	
0.45 MPa, Unannealed	258	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	25	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	109	*	E-6/K	
RTI Elec				UL 746
0.750 mm	120		°C	
1.50 mm	120		°C	
3.00 mm	120		°C	
RTI Imp				UL 746
0.750 mm	85		°C	
1.50mm	85		°C	
3.00 mm	105		°C	
RTI Str				UL 746
0.750 mm	115		°C	
1.50 mm	120		°C	
3.00 mm	120		°C	

Electrical	dry	cond.	Unit	Test Standard
Volume Resistivity (1.00 mm)	1E11	-	Ohm*m	IEC 60093
Dielectric Strength (1.00 mm)	27	24	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	5			ASTM D 495
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0			
1.50 mm	PLC 0			
3.00 mm	PLC 0			
High Voltage Arc Tracking Rate (HVTR), 3.00 mm	PLC 1			UL 746
Hot-wire Ignition (HWI)				UL 746
0.400 mm	PLC 4			
0.750 mm	PLC 4			
1.50 mm	PLC 4			

©2025 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Flammability	Value	Test Standard
Flammability		UL 94
0.750 mm	HB	
1.50 mm	HB	
3.00 mm	HB	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C
Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C
Mold Temperature	65 - 95	°C



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.