

Stanyl® HFX82S

PA46–GF45 FR(40)

45% Glass Reinforced, Halogen free and free of red phosphorous

Print Date: 2024–12–10

Stanyl® HFX82S is an electro–friendly & halogen–free flame–retarded high heat polyamide that offers an excellent combination of high CTI, flow and weld–line strength. HFX–grades are often used in connectors such as USB type C.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
DRY / COND			
Molding shrinkage (parallel)	0.3 / *	%	ISO 294–4
Molding shrinkage (normal)	0.9 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
DRY / COND			
Tensile modulus	15200 / 10300	MPa	ISO 527–1/–2
Tensile modulus (120°C)	7700 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	6500	MPa	ISO 527–1/–2
Stress at break	180 / 130	MPa	ISO 527–1/–2
Stress at break (120°C)	100 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	80	MPa	ISO 527–1/–2
Strain at break	2.2 / 2.8	%	ISO 527–1/–2
Strain at break (120°C)	3.5 / –	%	ISO 527–1/–2
Strain at break (160°C)	3.5	%	ISO 527–1/–2
Flexural modulus	14000 / 10200	MPa	ISO 178
Flexural modulus (120°C)	8300	MPa	ISO 178
Flexural modulus (160°C)	7300	MPa	ISO 178
Flexural strength	255 / 195	MPa	ISO 178
Flexural strength (120°C)	150	MPa	ISO 178
Flexural strength (160°C)	120	MPa	ISO 178
Charpy impact strength (+23°C)	70 / –	kJ/m²	ISO 179/1eU

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Stanyl[®] HFX82S

Print Date: 2024-12-10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Charpy notched impact strength (+23°C)	13 / –	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	286 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	276 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	282 / *	°C	ISO 75-1/-2
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	–	–
ELECTRICAL PROPERTIES		DRY / COND	
Electric strength	40 / –	kV/mm	IEC 60243-1
Comparative tracking index	600 / –	V	IEC 60112
Relative permittivity (1GHz)	4.2 / 4.4	–	IEC 61189-2-721
OTHER PROPERTIES		DRY / COND	
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1600 / –	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.