

Stanyl[®] TW200F5

PA46–GF25

25% Glass Fiber Reinforced, Heat Stabilized

Print Date: 2025–03–11

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		DRY / COND	
Molding shrinkage [parallel]	0.6 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	1.6 / *	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES		DRY / COND	
Tensile modulus	8700 / 4900	MPa	ISO 527–1/–2
Tensile modulus (120°C)	4700 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	4300	MPa	ISO 527–1/–2
Stress at break	195 / 110	MPa	ISO 527–1/–2
Stress at break (120°C)	105 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	93	MPa	ISO 527–1/–2
Strain at break	3.5 / 8	%	ISO 527–1/–2
Strain at break (120°C)	7 / –	%	ISO 527–1/–2
Strain at break (160°C)	7	%	ISO 527–1/–2
Flexural modulus	8000 / 4600	MPa	ISO 178
Flexural strength	255 / 130	MPa	ISO 178
Charpy impact strength (+23°C)	59 / 100	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	54 / 66	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	9.5 / 17	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	8.7 / 8.6	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	295 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	280 / *	°C	ISO 75–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Stanyl® TW200F5

Print Date: 2025-03-11

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7 / *	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES	DRY / COND		
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.