

VECTRA® S135

Liquid Crystal Polymer

35% glass reinforced Vectra grade with very low outgassing, very high heat deflection temperature (335 °C) and stiffness. Typical applications are lamp sockets, lens holders for beamers, electrical and electronic parts like connectors, relays, switches, coil bobbins and also under the hood applications.

Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 in natural at 0.28mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130 °C, mechanical 130 °C. UL = Underwriters Laboratories (USA)

Product information

Resin Identification	LCP-GF35	ISO 1043
Part Marking Code	>LCP-GF35<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.1 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.4 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	16000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	150 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.3 %	ISO 527-1/-2
Flexural modulus	16000 MPa	ISO 178
Flexural strength	240 MPa	ISO 178
Flexural strain at failure	2 %	ISO 178
Compressive strength	177 MPa	ISO 604
Compressive stress at 1% strain	114 MPa	ISO 604
Charpy notched impact strength, 23 °C	14 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	14 kJ/m ²	ISO 180/1A
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10 °C/min	350 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	340 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	267 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	5.8 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	57.5 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
-------------------------------	-----------	-----------------

Electrical properties

Relative permittivity, 1MHz	3.5	IEC 62631-2-1
Dissipation factor, 1MHz	90 E-4	IEC 62631-2-1
Volume resistivity	1E15 Ohm.m	IEC 62631-3-1
Surface resistivity	1E17 Ohm	IEC 62631-3-2
Electric strength	37 kV/mm	IEC 60243-1

VECTRA® S135

Liquid Crystal Polymer

Physical/Other properties

Humidity absorption, 2mm	0.002 %	Sim. to ISO 62
Water absorption, 2mm	0.014 %	Sim. to ISO 62
Density	1670 kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	150 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.01 %
Melt Temperature Optimum	375 °C
Min. melt temperature	370 °C
Max. melt temperature	380 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Back pressure	3 MPa
Ejection temperature	268 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Flame retardant, Heat stabilised or stable to heat, High Flow, Lead-free soldering resistant

Additional information

Injection molding

Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra S-grades should be dried at 150 °C for a minimum of 6 hours or at 170 °C for a minimum of 4 hours in a desiccant dryer.

Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: ½ feed, ¼ compression, ¼ metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

Processing Notes

Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew

VECTRA® S135


Liquid Crystal Polymer

point should be $\leq -40^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V (≤ 24 h).


Stress-strain



VECTRA® S135

Liquid Crystal Polymer

Secant modulus-strain



NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.